



SlipSmart Australia

ABN: 60 341 526 043

18 Stacer Street Upper Coomera, QLD 4209

Mob: 0410 657 399

email: info@slipsmartaustralia.com.au



Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.*

35 Dividend Street , Mansfield QLD 4122

Test Site: *Laboratory Tests Tru Plank Elite – Provincial Fawn*

Report Number: W1124

Date Tested: 02/02/2022

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: **MJS Floorcoverings Pty. Ltd. – Kerry Krebs,**


35 Dividend Street , Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Elite – Provincial Fawn 2.5mm x 228mm x 1524mm 0.7mm wear layer*

Standard Applied:	AS 4586-2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. 2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above. 4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited. 5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.						
Rubber Type:	Slider 96							
Fixed or unfixed surface:	Unfixed							
Cleaning type:	Nil							
Topography:	Lab							
Accelerated wear (if appropriate):	n/a	Environmental Conditions:	Fine, Dry	Date tested:	02/02/2022			
Slope:	n/a	Temperature:	23°C	Job Number:	W1124			
Sample Tested		Air Temp. °C	Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification
Test area #1		23	2.5mmx228x1524mm vinyl	Nil	48	47	00	P4
Test area #2		23	2.5mmx228x1524mm vinyl	Nil	47			
Test area #3		23	2.5mmx228x1524mm vinyl	Nil	44			
Test area #4		23	2.5mmx228x1524mm vinyl	Nil	45			
Test area #5		23	2.5mmx228x1524mm vinyl	Nil	49			

Other observations:

Remarks: *Sample details supplied by Client

Signatory 
Brent Vounechis

Peter Vounechis

Tested By: B Vounechis

