

X40 ACOUSTIC PANEL SPRAY ADHESIVE



DATA SHEET
TensorGrip



Developed in conjunction with the Acoustic industry, X40 is a web spray adhesive designed for use in fabricating acoustic wall panels.

PRODUCT DESCRIPTION

Tensor Grip® X40 is developed in conjunction with the acoustic industry for all acoustic panel bonding applications. Tensor Grip X40 is a fast drying contact adhesive, suitable for all types of acoustic panel installation and applications including in-house and on-site bonding processes.

ADVANTAGES

- Non-Flammable Adhesive
- Low VOC
- Excellent High Coverage of up to 230m² per 22ltr canister
- 80% of Final Strength achieved immediately upon bonding
- Can be tinted for visibility of application coverage
- Full strength achieved in 24 hours, high strength long-term bond
- Fast drying 3-4 mins with excellent initial green strength bond
- High tack – adheres aggressively to most surfaces
- Long open time 60 mins
- High (85°C) temperature heat resistant
- Low Odour – suitable for Building Sites
- Low Atomisation limiting overspray
- Portable Airless self sufficient Aerosol Canister Spray System with adjustable spray patterns

DIRECTIONS FOR USE

- Prepare panel and substrate for **TensorGrip® X40** adhesive application. Make sure that surfaces are clean, dry and free from dirt, dust, oil, loose paint, wax or grease, etc. Apply **TensorGrip® X40** adhesive to both the panel and substrate surfaces in an even manner with 80-100% surface coverage. Spray the pattern with a 50% overlap on passes of spray pattern holding the spray gun within 150mm of the surface being sprayed Using a spray-release-spray method to avoid excessive build up of overlapped adhesive patterns. Cutting in can be done by adjusting the spray gun to a smaller fan width spray pattern to allow for intricate spraying Porous surfaces may need a second coat, if needed, allow for first coat to tack-off before applying the second coat.
- Allow enough time for the glue line to tack-off (3-5 Minutes or until dry but tacky to the touch without any transfer of wet adhesive to fingers) before placing panels and creating the bond. Apply the panel to create the bond within the open time of the Tensor Grip X40 adhesive (within 60 minutes). If you have exceeded the open time, spray a fresh glue line and adhere within the open time. Full Surface pressure must be applied to bonded panel using a laminate type roller within 10 minutes of the panel being applied to facilitate full adhesive transfer and a strong bond. Initial bond is strong enough to allow for cutting or trimming immediately if needed The bonded panel should be smooth and free of air bubbles, wrinkles, gaps and or blemishes.
- Maximum bond strength is achieved with coverage of 100% and recommended coat weight of 20 dry grams per M².
- **NOTE:** For applications above head height a perimeter bead of construction adhesive, such as INSTA_GRIP X40, must be used in conjunction with this product.
- Clean any surface as necessary with the Tensor Citrus Based C101 bio-degradable adhesive cleaner and remover

CANISTER STORAGE/CHANGE OVER

- If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.
- To change or disconnect canister: turn canister valve to the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister.
- Reconnect the spray hose to a new canister of adhesive. OR if you are NOT connecting to a new canister, connect hose to canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean.

QUIN GLOBAL AU

63 Hinckman St. Queanbeyan NSW 2620

PH: 02 6175 0574 | sales@quinglobal.com | www.quinglobal.com

QUIN
GLOBAL

Tensor®

X40 ACOUSTIC PANEL SPRAY ADHESIVE

DATA SHEET
Tensorgrip

SPECIAL PRECAUTIONS

For optimum results store canister above 18°C during use, but must always be above 10°C. Allow substrates to acclimatise to normal room temperature (18°C) for 48 hours before bonding. Do not exceed open time of the adhesive. Keep canister off cold concrete floors during use. If adhesive is expelled wet or as a jet, canister is too cold – move to warm environment and allow to thoroughly acclimatise before reusing.

CAUTION

- Use only in well ventilated areas.
- Do Not thin or reactivate with solvents.
- Do Not incinerate.
- Do Not expose to extreme heat over 50°C.
- Keep away from sources of ignition.
- Release pressure before disconnecting hose.
- Test for suitability before use.

MSDS and Technical Data Sheets MUST be read and understood before use. Information contained in this technical literature is believed to be accurate and offered in good faith for the benefit of the consumer. The company however cannot assume any liability or risk involved in the use of its chemical products since the conditions of use are beyond our control. Statements concerning the possible use of our products are not intended as recommendations to infringe on any patent. These products are for industrial use only.

CHEMICAL TECHNICAL DATA

TYPICAL PROPERTIES

Total Solid:	21-27%
VOC Content:	Low VOC according to Green Star Office Interiors V1.1 IEQ-11
Colour:	Clear, Green
System Flammability:	Non-Flammable Adhesive; Flammable (2) Propellant
Solvent System:	Methylene Chloride
Dry time:	3-5 mins dependent on temp & humidity
Open time:	Extended - Bond within 60 minutes
Shelf Life:	18 months from date of manufacture

PACKAGING

• 500ml	Aerosol Can
• 22L	Disposable Canister
• 220L	Returnable Canister

STORAGE

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- Do Not store at temperatures over 50°C.
- Avoid exposure to direct sunlight.
- Do Not store directly on concrete floor.
- For optimum performance, store at 18°C during use, but must always be above 15°C.
- When connected, keep valve open and hose pressurised at all times.
- Do Not close valve until ready to connect to new cylinder.
- Release pressure in hose before disconnection.
- Always test Tensorgrip X40 to determine suitability for your particular application prior to use in production.

Copyright © 2017 by Quin Global AU Ltd All rights reserved. This publication or any portion thereof may not be reproduced or used in any manner whatsoever without the express written permission of the publisher.

DISCLAIMER OF WARRANTY: The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

QUIN GLOBAL AU

63 Hincksman St, Queanbeyan NSW 2620
PH: 02 6175 0574 | sales@quinglobal.com | www.quinglobal.com

QUIN
GLOBAL

Tensor[®]